

**TECHNICAL
INFORMATION**



Rainbow Dry Patch



PRODUCT

Rainbow Dry Patch is a 20kg bag factory blended, acrylic render, suitable for application to cement sheeting. Rainbow Dry Patch, will give flexibility whilst achieving high adhesion and strength.

SURFACE & PRODUCT PREPARATION

It is imperative that the substrate Rainbow Dry Patch is to be applied to is totally clean and removed of all loose particles, such as dirt, dust, etc. Failure to do so can cause delamination resulting in damage to the finish product. Insulcon takes no responsibility for problems arising from this.

In a clean bucket add approx 3 litres of clean water. Then whilst mixing with a mechanical mixer, add contents of Rainbow Dry Patch bag into the bucket. You may need to add some more Rainbow Dry Patch if you find the mixture to be too wet, or add some more water if you find the mixture too dry. A nice paste mix is the desired finish to achieve maximum results, both in finish and application.

If the mixture is too wet, it can be very messy and difficult to apply, resulting in hanging too long on the wall, making floating very hard and time consuming. If the mixture is too dry then it will be very difficult to apply as it will not glide on the wall and will tear when floating. This can also have an effect on drying time, resulting in a compromised fast cured product.

COVERAGE

When Rainbow Dry Patch is applied according to manufacturers instructions, Rainbow Dry Patch will cover approx 8-10 square metres
Note - These areas may vary depending on quality of substrate. Ideal application thickness of 2-4mm is recommended. This may also vary depending on substrate.



Insulcon Pty Ltd
34 Swift Way
Dandenong South
VIC, 3175

Ph : 9768 2335
Fax: 9768 2337
E-mail: sales@insulcon.com.au
Web : insulcon.com.au

**TECHNICAL
INFORMATION**



Rainbow Dry Patch



Insulcon Pty Ltd
34 Swift Way
Dandenong South
VIC, 3175

Ph : 9768 2335
Fax: 9768 2337
E-mail: sales@insulcon.com.au
Web : insulcon.com.au

APPLICATION

Insulcon recommends Rainbow Patch (not DryPatch) be applied to all the substrate joints with a 50mm fiberglass reinforced alkali resistant mesh imbedded. These joints need to be allowed time to fully dry. Once dry, using a steel trowel, apply Rainbow Dry Patch with a nice even coverage over the entire substrate. Rainbow Dry Patch then needs to be allowed time to dry partially, when at this time the surface needs to be floated.

This will be the base coat on which the texture coating will be applied. Any imperfection in this coat will be HIGHLIGHTED in the resultant product when texturing is complete.

Insulcon warns Rainbow Dry Patch should be allowed a minimum 5-7 days to cure completely before any finish coat (texture or membrane) is applied.

Warranties will be void if this has not taken place.

Rainbow Dry Patch should only be applied in suitable weather. Rain, freezing, excessive warmth and windy conditions are not suitable conditions for Rainbow Dry Patch application. Rainbow Dry Patch can be assisted in its curing, by putting some moisture back into the wall when the product has dried. Meaning, spray the wall with a slight mist as this will enhance the curing of the materials leaving a superior finish.

SAFETY

If swallowed: Rinse mouth and lips with water. Seek medical advice if discomfort occurs.

If in Eyes: Flush eyes thoroughly with flowing water for 15 minutes.

Seek medical attention symptoms persist.

If on skin: Wash thoroughly with soap and water.

If Inhaled: Remove subject to fresh air. If symptoms persist seek medical attention.