

**TECHNICAL
INFORMATION**



Rainbow Patch



PRODUCT

Rainbow Patch is a top of the range acrylic patching compound, which cures to an excellent finish that retains some flexibility, has a high adhesion and excellent durability. Rainbow Patch is perfect for skim coating and patching joints in cement and blueboard sheeting applications. Rainbow Patch is also ideal for patching joints in pre rendered panels.

SURFACE & PRODUCT PREPARATION

Rainbow Patch comes pre mixed in a 15 litre drum. Addition of a pinchful of cement whilst Rainbow Patch is on the applicators hawk is recommended. This will help the curing properties and ingredients of Rainbow Patch

It is imperative that the substrate Rainbow Patch is to be applied to is totally clean and removed of all loose particles, such as dirt, dust, etc. Failure to do so can cause delamination resulting in damage to the finish product. Insulcon takes no responsibility for problems arising from this.



COVERAGE

When Rainbow Patch is applied according to manufacturers instructions, Rainbow Patch will cover approx 11-13 square metres skim coat on blueboard.

Note - These areas may vary depending on substrates and quality of substrates. Ideal application thickness of 2-3mm is recommended. This may also vary depending on substrate.



Insulcon Pty Ltd
34 Swift Way
Dandenong South
VIC, 3175

Ph : 9768 2335
Fax: 9768 2337
E-mail: sales@insulcon.com.au
Web : insulcon.com.au

**TECHNICAL
INFORMATION**



Rainbow Patch



APPLICATION

When using Rainbow Patch for jointing etc, it is to be applied using a steel trowel. Insulcon recommends that the Rainbow Patch be spread through the joint and reinforced fibre mesh imbedded into the Patch. (not adhesive mesh, then patch over the top)

When skim coating, Rainbow Patch is to be applied using a steel trowel with nice even coverage over the substrate. Rainbow Patch then needs to be allowed time in which it will start to dry slightly. At this time the surface needs to be floated with a plastic float.

This will be the base coat on which the texture coating will be applied to. Any imperfection in this coat will be HIGHLIGHTED in the resultant product when texturing is complete.

Insulcon warns Rainbow Patch should be allowed a minimum 5-7 days to cure completely before any finish coat (texture or membrane) is applied.

Warranties will be void if this has not taken place.

Rainbow Patch should only be applied in suitable weather. Rain, freezing, excessive warmth and windy conditions are not suitable conditions for Rainbow Patch application.

SAFETY

If swallowed: Rinse mouth and lips with water. Seek medical advice if discomfort occurs.

If in Eyes: Flush eyes thoroughly with flowing water for 15 minutes.

Seek medical attention symptoms persist.

If on skin: Wash thoroughly with soap and water.

If Inhaled: Remove subject to fresh air. If symptoms persist seek medical attention.



Insulcon Pty Ltd
34 Swift Way
Dandenong South
VIC, 3175

Ph : 9768 2335
Fax: 9768 2337
E-mail: sales@insulcon.com.au
Web : insulcon.com.au