

**TECHNICAL  
INFORMATION**



# Rainbow Texture 18/40



Insulcon Pty Ltd  
34 Swift Way  
Dandenong South  
VIC, 3175

Ph : 9768 2335  
Fax: 9768 2337  
E-mail: [sales@insulcon.com.au](mailto:sales@insulcon.com.au)  
Web : [insulcon.com.au](http://insulcon.com.au)

## PRODUCT

Rainbow Texture is a **100% RUST FREE** trowel applied acrylic decorative finish. Rainbow Texture comes in a 15 litre pail, pre mixed ready to use straight from the pail. Rainbow texture can easily be tinted to almost any colour from the most popular of colour ranges available.

## SURFACE & PRODUCT PREPARATION

It is imperative that the substrate Rainbow Texture is to be applied to is totally clean and removed of all loose particles, such as dirt, dust, etc. Failure to do so can cause delamination resulting in damage to the texture coating.

Although Rainbow Texture is ready to use straight from the pail, Insulcon recommends the texture be agitated with a mixer before use to achieve maximum results.

***NOTE—Please make sure base coat has been allowed 5-7 days to cure before application of Rainbow Texture.***

***\*Failure to do so can have drastic effects on the finished product.***

***\*Insulcon takes no responsibility if this has not occurred.***

## COVERAGE

When Rainbow Texture is applied according to manufacturers instructions, Rainbow Texture will cover approx 10-11 square metres. This may vary due to surface condition and absorption effects.

***NOTE— Any addition of sand, water etc to gain extra metres of application will have negative impact on the product and void any Insulcon warranty.***

**TECHNICAL  
INFORMATION**



# Rainbow Texture 18/40



Insulcon Pty Ltd  
34 Swift Way  
Dandenong South  
VIC, 3175

Ph : 9768 2335  
Fax: 9768 2337  
E-mail: sales@insulcon.com.au  
Web : insulcon.com.au

## APPLICATION

Rainbow Texture is to be applied using a steel trowel in a nice tight coat as thick as the aggregate will allow. Insulcon recommends a 2 man job but understand this cant always be possible. Whilst the Rainbow Texture is being trowelled, simultaneous floating of the applied texture is required. This must be done using a plastic float.

This floating process is vital in the success of the finished product. A common cause of a damaged job is when the applied texture has been left to long before floating has commenced resulting in a 'skin' forming on the texture. This cannot be reversed.

Insulcon warns Rainbow Texture should be allowed a minimum 5-7 days to cure completely before any membrane coat is applied. Warranties will be void if this has not taken place.

Rainbow Texture should only be applied in suitable weather. Rain, freezing, excessive warmth and windy conditions are not suitable conditions for Rainbow Texture application.

***\*Prior to texture works commencing, make sure a test panel has been carried out for approval of both texture and colour by client***

## SAFETY

- If swallowed: Rinse mouth and lips with water. Seek medical advice if discomfort occurs.
- If in Eyes: Flush eyes thoroughly with flowing water for 15 minutes.  
Seek medical attention symptoms persist.
- If on skin: Wash thoroughly with soap and water.
- If Inhaled: Remove subject to fresh air. If symptoms persist seek medical attention.